



Permits is a trading name of Textiles F.R. Ltd.

Unit 4B, (30) Wharfedale Road  
Euroway Trading Estate  
Bradford  
West Yorkshire  
BD4 6SG

# Textiles F.R. Limited

Flame Retardancy Finishers & Consultants

Tel: 01274 651230  
Fax: 01274 651305  
E-mail: sales@textilesfr.co.uk  
Web site: www.textilesfr.co.uk



## Test Report & Certificate

UKAS TESTING LABORATORY No.1413

British Standard Flammability Test Document: 21435 Page 1 of 1  
Test Method : BS EN ISO 15025:2002 Duplicate Document 1  
Specification: BS5867-2:2008:Type B Contract Curtain Test

Customer Account: BAN008  
BANNER WORLD  
UNIT 5  
BROOKSIDE CENTRE  
RED MARSH IND ESTATE  
THORNTON-CLEVELEYS  
FY5 4HD

Order Details  
TFR Order No : 253282  
Customer Order : EMAIL JL  
Order Date : 08/05/2019  
Fabric Description : DYE SUBLIMATION BLACK BCK  
Fabric Composition :  
Quantity (metres) : 1.0

Sample Conditioning : Test specimens were conditioned in an atmosphere having a temperature of 20°C +/- 2°C and Relative Humidity 65% +/- 5% for a minimum of 24 hours prior to testing.  
Test Enclosure Conditions : Temperature 20 °C Relative Humidity 65 %  
Cleansing Procedure : Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.  
Other Details :  
Sample Treatment : Sample tested in an as received state

Test Procedure:  
Six specimens were prepared each measuring 200mm +/- 2mm x 160mm +/- 2mm, three with the longer dimension in the length and three with the longer dimension in the width. A butane flame was applied to the sample face for 15 seconds.

Report Notes:  
This test was carried out in accordance with BSEN ISO 15025 Procedure A. The results may not apply to situations where there is a restricted air supply or prolonged exposure to large sources of heat such as in a conflagration.

OBSERVATIONS	Warp Direction			Weft Direction		
	Rep1	Rep2	Rep3	Rep1	Rep2	Rep3
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris	No	No	No	No	No	No

### Comments:

COMPLIANCE REQUIREMENTS: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen and there shall be no separation of flaming debris from any specimen.

The sample complied with the requirements for BS5867-2:2008:Type B  
Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.

Conducted by : Mr. J. P. MAGEE  
Laboratory Technician  
Authorised by: Miss K. BUTTON

Date 03/06/2019

Date 03/06/2019