



## TEST REPORT

No. : SC110520274

Date : Jun.25,2011

Page: 1 of 2


The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : Flex banner and pvc tarpaulin  
Test Required : Fire behavior test  
Test Method : DIN 4102-1-1998  
Manufacturer :   
Material and Mark :   
Date of Receipt : May.28,2011  
Test Period : May.28, 2011 to Jun.25,2011  
Test result(s) : Please refer to next page(s)

\*\*\*\*\* To be continued \*\*\*\*\*

COPY

Signed for SGS-CSTC Standards  
Technical Services Co., Ltd

  
Joanna Wang  
Lab Technical Supervisor

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not liberate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company.

## TEST REPORT

No. : SC110520274

Date : Jun.25,2011

Page: 2 of 2

Test result :

No.	Test Item	Standard require	Test result	Conclusion
①	Minimum residual length,(mm)	>0	378	Pass
②	Average residual length,(mm)	≥150	383	Pass
③	Average effluent temperature,(°C)	≤200	168	Pass
④	Flame height ,(mm)	<150, No molten dripper ignite the filter paper.	Meet the require	Pass

Test Item	Test Required	Conclusion
Fire behavior test	Class B1	Pass

\*\*\*\*\*End of report\*\*\*\*\*

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.